


STASSKOL



SK 101

Sealing material for all gases in non-lubricated and lubricated applications

SK101 is a sealing material based on Polytetrafluorethylene (PTFE) and it is widely used in lubricated as well as in dry-running service. A typical application is the compression of gases like Oxygen, Nitrogen, Air and Hydrocarbons mostly by reciprocating systems. The optimized content of glass fibers ensures high service life-times, increased mechanical properties and an improved chemical resistance.

TRIBOLOGICAL PROPERTIES

The tribological properties are defining the wear behavior of the material. The wear rate (k) and friction coefficient (μ) of SK101 are identified by tribological characterization.

Under Air	
Wear rate:	$k = 2 \cdot 10^{-6} \text{ mm}^3/\text{Nm}$
Friction coefficient:	$\mu = 0.24$

The following conditions were applied during the test of SK101:

Gas:	Air
Average velocity:	2.7 m/sec
Pressure:	20 bar
Dew point:	13 °C
Counter surface:	steel with tungsten carbide coating
Lubricant:	none

The lower the wear rate the higher are the wear resistance and the expected service life-time at the field application.

STASSKOL provides state-of-the-art equipment for tribological characterizations under reciprocating and rotating movement. An unique reciprocating tribometer was used to investigate the wear behavior of SK101.



The material performance strongly depends on the test conditions. Therefore measurements at the parameters of the customer's application are recommended. Please use the characterization and development capabilities of STASSKOL.

MECHANICAL PROPERTIES

SK101 shows an increased stiffness due to the high filler content. The mechanical properties have been investigated using a tensile testing machine under standard (DIN EN ISO 527-1) conditions.

Elastic modulus:	590 MPa
Tensile strength:	20.1 MPa
Elongation at break:	290 %
Density:	2.23 g/cm ³
Hardness:	46.0 Shore D

CUSTOMER GUIDELINE

Operating Conditions:

Dry-running or lubricated
Pressure up to 200 bar
Temperature up to 150 °C
Average velocity up to 4,5 m/sec
Dew point down to -50 °C

References:

Refinery applications
Air filling stations
Air guns (SEISMIC)
Oxygen compressors

Please contact STASSKOL to get additional information about SK101. You will be supported by choosing the best sealing material according to the operating conditions of your application.

STASSKOL Inc.
19911 Morton Road, Suite 200
Katy, Texas 77449
USA

☎ +1-713-244-5050
✉ info@stasskol.com

STASSKOL GmbH
Maybachstrasse 2
39418 Stassfurt
Germany

☎ +49-3925-288-100
✉ info@stasskol.de

🌐 www.stasskol.com