

STASSKOL



SK901

Sealing material for high temperatures and pressures
in non-lubricated and lubricated applications

SK901 is a sealing material based on Polyetheretherketone (PEEK) and it is widely used in dry-running as well as in lubricated service. A typical application is the compression of gases like Hydrogen, Nitrogen and Hydrocarbons mostly by reciprocating systems. The optimized content of Carbon fibers, Polymeric fillers and Graphite ensures high service life-times, increased mechanical properties and an improved chemical resistance.

TRIBOLOGICAL PROPERTIES

The tribological properties are defining the wear behavior of the material. The wear rate (k) and friction coefficient (μ) of SK901 are identified by tribological characterization.

Under Hydrogen	
Wear rate:	$k = 2 \cdot 10^{-7} \text{ mm}^3/\text{Nm}$
Friction coefficient:	$\mu = 0.08$

The following conditions were applied during the test of SK901:

Gas:	Hydrogen
Average velocity:	2.7 m/sec
Pressure:	20 bar
Dew point:	-90 °C
Counter surface:	steel with tungsten carbide coating
Lubricant:	none

The lower the wear rate the higher are the wear resistance and the expected service life-time at the field application.

STASSKOL provides state-of-the-art equipment for tribological characterizations under reciprocating and rotating movement. An unique reciprocating tribometer was used to investigate the wear behavior of SK901.



The material performance strongly depends on the test conditions. Therefore measurements at the parameters of the customer's application are recommended. Please use the characterization and development capabilities of STASSKOL.

MECHANICAL PROPERTIES

SK901 shows an increased stiffness due to the high filler content. The mechanical properties have been investigated using a tensile testing machine under standard (DIN EN ISO 527-1) conditions.

Elastic modulus:	5,650 MPa
Tensile strength:	81.3 MPa
Elongation at break:	2.3 %
Density:	1.45 g/cm ³
Hardness:	142 Shore D

CUSTOMER GUIDELINE

Operating Conditions:

Dry-running or lubricated
Pressure up to 400 bar
Temperature up to 250 °C
Average velocity up to 4.5 m/sec
Dew point down to "bone-dry"

References:

Refinery applications
Hydrogen compressors
Natural gas stations
Biogas applications

Please contact STASSKOL to get additional information about SK901. You will be supported by choosing the best sealing material according to the operating conditions of your application.

STASSKOL Inc.
19911 Morton Road, Suite 200
Katy, Texas 77449
USA

☎ +1-713-244-5050
✉ info@stasskol.com

STASSKOL GmbH
Maybachstrasse 2
39418 Stassfurt
Germany

☎ +49-3925-288-100
✉ info@stasskol.de

🌐 www.stasskol.com