STASSKOL

Innovative Solutions for Reliable Reciprocating Compressor Application

Application

Gas: Suction Pressure: Discharge Pressure: Suction Temperature: Discharge Temperature: Gas Mix (30 % HCl; 70 % Fluorocarbons) 0.05 barg / 0.73 psig 17.30 barg / 252 psig 35 °C / 95 °F 140 °C / 284 °F

FailureMode

Swelling of packing internals. Temperatures increase during operation.



Root Cause

PTFE-compound is not suitable when fluorinated gases are compressed. The PTFE parts where chemically solved by process gas.

Solution

Material change from PTFE compound SK301to PEEK SK901. Such the operating temperatures could be dropped and the running time of the internals could be increased significantly.



Swollen sealing rings

FIELD CASE Packing Internals

STASSKOL, Inc.

19911 Morton Rd., Suite 200 Katy, Texas 77449 USA Phone: +1 713 244 5050 Mobile: +1281 91 0567 Web: www.stasskol.com

STASSKOL GmbH

39418 Stassfurt Maybachstrasse 2 Germany Phone: +49 3925288 100 Mail: info@stasskol.de Web: www.stasskol.de